



H8101D Photoluminescent Egress Tape

Subject	Result
Back carrier	0.15mm PVC
Total applied thickness	0.79mm
Type of adhesive	Solvent acrylic
Adhesive thickness	0.06mm±0.01mm
Release paper thickness	0.17mm±0.01mm
Adhesion to steel	1.5kg/25.4mm↑
Tensile strength	4kg/25.4mm↑
Elongation at break	25%↑
Temperature range	-5°C to +50°C

Luminance test	
Time (minutes)	Luminance (mcd/m ²)
2	478.4
10	95.1
30	27.7
60	12.17
Decay time (to 0.3mcd/m ²)	1450 mins

All the above data is for reference only.
©Heskins Ltd 1997-2018