



ANTI-SLIP SOLUTIONS
mail@heskins.com

www.heskins.com

20/02/2017

Heskins H8152 Premium Grade Egress Tape

Physical Characteristics

Subject	Result
Composition	PET
Type of adhesive	Pressure sensitive
Overall thickness (mm)	0.37mm
Glow Time	8-10 Hours
Temperature range	-30°C ~ 90°C
Maximum roll size	1240mm x 50m
Colour (Daylight)	Greenish Yellow
Glowing Colour	Bright green

Photoluminescent performance*

Time	Luminance (mcd/m ²)	Test date
10 minutes	222	20/02/17
60 minutes	27	20/02/17
Decay time to 0.3 mcd/m ² > 600 minutes		

DIN 67510

The above tests were conducted in accordance with ASTM 2072. Test Method E 2073, shall be not less than: 20.0 mcd/m² at 10 min after activation has ceased; and 2.8 mcd/m² at 60 min after activation has ceased.

All the above data is for reference only.

©Heskins Ltd 1997~2017

