

PermaStripe® data sheet

Subject	Result	Test method
Plastic composition	PVC	N/A
Plastic thickness	1mm	N/A
Peel adhesion N/25mm	42.2	180° FINAT FTMI
Tensile strength, N/25mm	>200	Lloyd 500N load cell
Adhesive thickness	0.2mm	N/A
Total thickness	1.3mm	N/A
Initial tack (cm)	< 8	PSTC-6
180° Adhesion (kg/25.4mm)	>1.8	ASTM-D1000
Holding Power (hrs/kg/25.4mm ²)	>48	PSTC-7
Temperature range	-30°C to +70°C	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England.

	Coefficient of Friction category	Test
H6901 PermaStripe	R10	DIN51130

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request.

All the above data is for reference only.

©Heskins Ltd 1997-2018