

Specification reference: H8101C

Subject	Result
Back carrier	0.15mm PVC
Total applied thickness	0.79mm
Type of adhesive	Solvent acrylic
Adhesive thickness	0.06mm±0.01mm
Release paper thickness	0.17mm±0.01mm
Adhesion to steel	1.5kg/25.4mm↑
Tensile strength	4kg/25.4mm↑
Elongation at break	25%↑
Temperature range	-5°C to +50°C

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

H8101C Luminance Measurements

Luminance times	Mcd/m ²
2	478.4
10	95.1
30	27.7
60	12.2
120	5.5
1450	0.3

©Heskins Ltd 1997-2017