

## Heskins Ltd H3408 Cushion Grip data sheet

Subject	Result
Components	PU51% Polyester 49%
Colour	Grey
Adhesive Base	Acrylic
Thickness	1mm
Initial Tack	20# Ball
Applied Weight	641 g/m <sup>2</sup>
180° Peel Adhesion	1.5 kg/in
Holding Power 25°C	1 in 1.0kg > 24hrs
Temperature Range	-10°C ~ 80°C
Bursting Strength	10kg/cm <sup>2</sup>
Abrasion Stoll	800 Cycles
Elongation	Without PET: 10% With PET: 5%

### LRV Test Results

Material/Colour	Av. LRV	Range
H3408S (Grey)	20.25	2

*The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.*

All the above data is for reference only.

©Heskins LTD 1997-2022