



ANTI-SLIP SOLUTIONS  
[mail@heskins.com](mailto:mail@heskins.com)

[www.heskins.com](http://www.heskins.com)

13/11/2023

## Heskins H3415 coarse resilient data sheet

Subject	Result
Composition	PVC upper and PET base
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.3mm
Tackloop (kg/25.4mm)	6.23
Cohesion (minutes/25°C)	2812↑
Adhesion to steel (kg/25.4mm)	5.714
Temperature range	-30°C ~ 80°C
Maximum roll size	1371mmx100m
Life (months)	12 to 24

### LRV Test Results

Material/Colour	Av. LRV	Range
H3415N (Black)	0.5	1
H3415S (Grey)	5.75	1
H3415W (White)	78.5	1
H3415T (Transparent)	47.5	12
H3415Y (Yellow)	44.5	1

### Coefficient of friction data

	Dry surface test result	Wet surface test result
EN16165:2021 Pendulum Test Value (PTV)	0.95	0.6
DIN51130	R10	
NFSI	High traction	

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2023

