

Heskins Printed Safety Grip data sheet

Specification reference: H3417

Subject	Result	Test method
Back carrier	0.1mm PVC	Calliper method
Total applied thickness	0.7mm	Calliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (g/25.4mm ²)	1500↑	PSTC-4
Tensile strength (Kg/25.4mm ²)	6.0↑	PSTC-31
Tear resistance (g)	5600 +/- 200	PSTC-39
Peel adhesion, N/25mm	23.5	180° FINAT FTMI
Tensile strength, N/25mm	68.0	Lloyd, 500N load cell
Elongation at break	25%↑	PSTC-31
Temperature range	-30°C to +70°C	See notes below
Maximum size of production roll	1168mm x 100m	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Coefficient of friction data

Safety-Grip®	Dry surface test result	Wet surface test result
Standard	102 TRL	71 TRL

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

LRV Test Results

Material/Colour	Av. LRV	Range
H3417-B/Y	44.69	3.6

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.



ANTI-SLIP SOLUTIONS

Email: mail@heskins.com

Website: www.heskins.com
All the above data is for reference only.
©Heskins Ltd 1997-2022

Date: 17/03/2022

