

Heskins Ltd H3422 Skateboard Grip Tape data sheet

Subject	Result	Test method
Back carrier	0.12m PVC	Calliper method
Total applied thickness	0.76mm	Calliper method
Type of adhesive	Solvent acrylic	N/A
Adhesion to steel (g/25.4mm ²)	1500↑	PSTC-4
Tensile strength (Kg/25.4mm ²)	6.0↑	PSTC-3I
Elongation at break	25%↑	PSTC-3I
Temperature range	-30°C to +70°C	See notes below
Maximum size of production roll	1168mm x 100m	N/A

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Coefficient of friction data

Safety-Grip®	Dry surface test result	Wet surface test result
Standard	102 TRL	71 TRL

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests, we also have results ASTM C 1028-96.

LRV Test Results

Material/Colour	Av. LRV	Range
H3422 (Black)	2.62	1.68

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins LTD 1997-2022