

Heskins H3435 Ribbed Rubber data sheet

Subject	Result	Test method
Back carrier	1.6mm ribbed PVC & PET composition	Caliper method
Total applied thickness	1.7mm	Calliper method
Adhesive thickness	0.1mm	Caliper method
Type of adhesive	Solvent acrylic	N/A
Tack loop (1kg/25.4mm)	6.268	PSTC-16
Cohesion (hrs/25°C)	24↑	ASTM-7
Adhesion to steel (1kg/25.4mm)	2.696	PSTC-1
Maximum size of production roll	1194mmx18.3m	N/A

Coefficient of Friction

	Dry surface test result	Wet surface test result
H3435	116	30

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, copy certificates are available on request. Tests performed using TRL test vehicle, Four S test data also available if required.

LRV Test Results

Material/Colour	Av. LRV	Range
H3435N (Black)	1.07	1.8

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.
©Heskins Ltd 1997-2022