

H3470 TackyGrip data sheet

Subject	Result
Upper Film:	Elastomeric polymer
Base Film:	PET
Upper Film Thickness:	0.7mm
Total Thickness:	0.75mm
Phthalates	0%
Adhesion:	25N/25mm
Cohesion:	Very high
Widths:	6mm up to 1220mm
Lengths:	18.3mm, others on request
Adhesive	Transparent modified acrylic
Temperature range	-30° to +70°C

Coefficient of friction

Angle	69°
Static Coefficient of Friction, dry (SCoF)	2.6
Lab verdict	Potentially good grip

The above Coefficient of Friction test was performed by Sotter Engineering Corporation, Floor Friction Testing division., California. Certificates on request.

All the above data is for reference only.

© Heskins Ltd 1997-2020