



ANTI-SLIP SOLUTIONS
mail@heskins.com

www.heskins.com

30/03/2021

Heskins H540I coarse resilient data sheet, 2mm thick

Subject	Result
Composition	PVC upper and PET base
Type of adhesive	Solvent acrylic
Overall thickness (mm)	2mm
Tackloop (kg/25.4mm)	6.23
Cohesion (minutes/25°C)	2812↑
Adhesion to steel (kg/25.4mm)	5.714
Temperature range	-10°C ~ 80°C
Maximum roll size	1346mmx100m
Life (months)	12 to 24

Coefficient of friction data

	Dry surface test result	Wet surface test result
H540I Coarse resilient	95 TRL	60 TRL

LRV Test Result

Material/Colour	Av. LRV	Range
H540IB (Blue)	6.42	0.74
H540IY (Yellow)	55.51	1.47
H540IS (Grey)	19.54	0.84
H540IN (Black)	1.65	0.66

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2021

