

## H6904 PermaCover Data Sheet

Subject	Result
<b>Upper film</b>	Clear PVC 0.5mm
<b>Adhesive base</b>	Red PET, 0.21mm
<b>Adhesive type</b>	Modified solvent acrylic
<b>Initial Tack (No/Ball)</b>	#30
<b>180° Peel Adhesive (kg/25mm)</b>	3.5 ↑
<b>Holding Power (hr/kg*25mm<sup>2</sup>)</b>	24 ↑

### LRV Test Results

Material/Colour	Av. LRV	Range
H6904T (Clear)	20.08	16.08

*The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.*

All the above data is for reference only.

©Heskins LTD 1997-2022