

H6906 PermaStripe® Smooth data sheet

Subject	Result	Test method
Plastic composition	PVC	N/A
Plastic thickness	1mm	N/A
Peel adhesion N/25mm	42.2	180° FINAT FTMI
Tensile strength, N/25mm	>200	Lloyd 500N load cell
Adhesive thickness	0.2mm	N/A
Total thickness	1.3mm	N/A
Initial tack (cm)	< 8	PSTC-6
180° Adhesion (kg/25.4mm)	>1.8	ASTM-D1000
Holding Power (hrs/kg/25.4mm ²)	>48	PSTC-7
Temperature range	-30°C to +70°C	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England.

LRV Test Results

Material/Colour	Av. LRV	Range
H6906R (Red)	19.93	0.43
H6906O (Orange)	36.23	0.98
H6906Y (Yellow)	63.63	2.87
H6906V (Green)	30.08	0.98
H6906B (Blue)	20.98	1.1
H6906W (White)	88.5	0.09
H6906N (Black)	3.36	0.44
H6906D (Black)	2.97	0.5
H6906D (Yellow)	61.82	0.49
H6906A (Red)	25.19	1.08
H6906A (White)	77.42	1.22

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins LTD 1997-2022