

Heskins Ltd H7502 Warehouse Markers data sheet

| Subject | Result | Test method |
|--|---------------------------|-----------------|
| Material | PVC laminated with DST | N/A |
| Type of adhesive | Solvent acrylic (0.082mm) | N/A |
| PVC | 0.3mm rigid film | N/A |
| DST | 0.095mm | N/A |
| Initial tack (cm) | 12 | PSTC-6 |
| Peel adhesion (kg/25.4mm) | 1.3 | PSTC-1 |
| Holding power (hr/25.4mm²) | 1↑ | PSTC-7 |
| Resistance to water (months) | 10 | PSTC-35 |
| Resistance to chemicals (months) | 8 | PSTC-35 |
| Resistance to motor oil | Excellent | PSTC-35 |
| Temperature range | -30°C ~ +70°C | See notes below |

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

LRV Test Results

| Material/Colour | Av. LRV | Range |
|-----------------|---------|-------|
| H7502 (Yellow) | 34.72 | 1.56 |

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins Ltd 1997-2022