

Heskins H780 I photoluminescent warehouse marker data sheet

Subject	Result	Test method
Material	Under surface printed OPP	N/A
Type of adhesive	Solvent acrylic (0.01mm)	N/A
Film thickness	0.041mm	N/A
Adhesive thickness	0.18mm	N/A
Total thickness	0.22mm	PSTC-6
Temperature range	-30°C ~ +70°C	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Luminance test	
Time (minutes)	Luminance (mcd/m ²)
2	478.4
10	95.1
30	27.7
60	12.17
Decay time (to 0.3mcd/m²)	1450 mins

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS:8493:2008+A1:2010

All the above data is for reference only.

©Heskins Ltd 1997-2023