

## Heskins H8101C Directional Egress Glow in the Dark data sheet

Subject	Result
Back carrier	0.15mm PVC
Total applied thickness	0.79mm
Type of adhesive	Solvent acrylic
Adhesive thickness	0.06mm±0.01mm
Release paper thickness	0.17mm±0.01mm
Adhesion to steel	1.5kg/25.4mm↑
Tensile strength	4kg/25.4mm↑
Elongation at break	25%↑
Temperature range	-5°C to +50°C

*The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)*

### H8101C Luminance Measurements

Luminance times	Mcd/m <sup>2</sup>
2	478.4
10	95.1
30	27.7
60	12.2
120	5.5
1450	0.3

### LRV Test Results

Material/Colour	Av. LRV	Range
H8101C (Glow in the Dark))	94.28	0.94
H8101C (Black)	8.91	2.25

*The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.*

*All the above data is for reference only.*

**©Heskins LTD 1997-2022**