

Heskins H9115 UHDBT (1.5mm) Data Sheet

Subject	Result	Test method
Adhesive	Acrylic	
Carrier	Acrylic Foam	
Colour	Grey	
Total thickness (mm)	1.50 ± 50 µm	ASTM-1000
Release liner	Red PE	
Maximum size of production roll	800mmx33m	
Tensile strength (gf/cm²)	6,000	ASTM D-897
Peel adhesion (gf/25mm)	4,500	ASTM D-3330
Holding power	> 24 hour	ASTM D-3654
Dynamic Shear Strength (gf/cm²)	Before 20 minutes ≥ 4,000 After 24 hours ≥ 6,000	ASTM D1002
Temperature max	≥100°C	

LRV Test Results

Material/Colour	Av. LRV	Range
H9915X (Red)	1	2

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins Ltd 1997-2022