HESKINS

ANTI-SLIP SOLUTIONS

mail@heskins.com www.heskins.com

23/04/2024

H3408S Cushion Grip Data Sheet

Subject	Result
Components	PU51% Polyester 49%
Colour	Grey
Adhesive base	Acrylic
Thickness	1mm
Initial tack	20# Ball
Applied weight	641 g/m²
180° Peel adhesion	1.5 kg/in
Holding power 25°C	1 in 1.0kg > 24hrs
Temperature range	-10°C ~ 80°C
Bursting strength	10kg/cm²
Abrasion stoll	800 Cycles
Elongation	Without PET: 10% With PET: 5%

Coefficient of Friction Data

Test	Dry Surface Test Result	Wet Surface Test Result	Test Standard
Pendulum (PTV)	1.02	0.71	EN 13036-4

The tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request.

LRV Test Results

SKU/Colour	RAL	Pantone	Av. LRV	Range
H3408S/Grey	7046	431 U	20.3	2

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins Ltd 1997-2024

ISO 9001 CERTIFIED UKAS MANAGEMENT SYSTEMS British Assessment Bureau
ISO 14001 CERTIFIED UKAS MANAGEMENT SYSTEMS British Assessment Bureau